

JT 7300 WG-PB 30

PRODUCT DESCRIPTION

Budget monomeric perforated window film self adhesive printing media.

Face Material: 180 µm white gloss PVC, 1.6 mm perforation, 30% open area

Adhesive: Solvent acrylic semi-permanent black

Liner: PE coat liner 135 gsm

TYPICAL USE

Short -term indoor and outdoor promotional graphics on flat smooth glass surfaces on buildings and vehicle windows for advertising.

PROCESSING

Especially designed for Solvent, eco-solvent and Latex inkjet printing on wide-format printing equipment.

To achieve optimal protection and durability, JT 7300 WG-PB 30 needs to be laminated with LUV 7036 or LF 10500 Series.

To achieve the best possible print quality, please make sure that the correct ICC profiles or printer settings are used.

Profiles can be obtained from our subsidiaries or distributors, or can be downloaded from: www.mactacgraphics.eu.

For further information on printing, application and removal, please refer to "TB 4.1 Guidelines on handling, converting and applying Mactac Digital media".

To ensure application suitability, always test the proposed construction under actual application and end-use conditions before going into full production.

SHELF LIFE

2 years when stored at 15 to 25°C and ± 50 % relative humidity (in the original packaging).

PHYSICAL PROPERTIES (TYPICAL VALUES)

Average Values Test Method

Thickness		
Film (microns)	180 μm	ISO 534
Adhesive data, 23°C (N/25 mm)		
Peel adhesion on glass		
Quick tack	6.5	FTM9
24 hour residence	6.5	FTM1
Dimensional stability		
Shrinkage (1 week at 70°C applied on Aluminium)	Max 0.5 mm	FTM14
Temperature ranges		
Minimum application temperature (°C)	+ 10°C	
Minimum application temperature (°C)	- 15 °C to + 60 °C	
Certifications		
Fire Classification	B-s2,d0	EN 13501-1

EXPECTED DURABILITY

Central Europe Zone 1

Unprocessed	1 year	ISO 4892-2
Printed & laminated*	Up to 2 years	ISO 4892-2

*For more information, refer to "TB 7.5 Outdoor Durability of Mactac Graphics - Self-adhesive films".

Note : Overlamination of the inkjet-printed material delays the eventual colour fading that may occur over time. This colour fading is dependent on the quality of the inkjet inks, the orientation of the printed material, the angle of display and the exact geographical location of exposure.

Exposure to severe temperatures, ultraviolet light, and/or conditions in Southern European countries, tropical, sub-tropical or desert regions will cause more rapid deterioration. This also applies to polluted areas, high altitudes and south-facing exposure.

DISCLAIMER

For more information on the durability and exposure please visit the "Mactac Technical Bulletin TB 7.5 Outdoor Durability of Mactac Graphics - Self-adhesive films" on the [www.https://www.mactacgraphics.eu](https://www.mactacgraphics.eu) website.

Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>. Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.